

## ABSC(X)

Silicon Carbide Long Venturi Nozzle with Polyurethane Jacket



**AIRBLAST**



### **ABSC(X)**

The ABSC(X) range comprises of Silicon Carbide lined long venturi nozzles with Polyurethane Jackets. The use of the Silicon Carbide liner reduces the weight of the nozzle by approximately 40% when compared to a standard nozzle of the same size – this reduces operator fatigue. Silicon Carbide is also a very durable nozzle liner providing increased operating life when compared to standard nozzle liners.

The ABSC nozzle has a 25 mm (1") inlet and the ABSCX has a 32 mm (1¼") inlet and are available with a standard large thread (/50).

Airblast high velocity venturi style nozzles have been designed to maximize blast cleaning rates and provide uniform abrasive distribution. The venturi design accelerates the air / abrasive mix as it exits the nozzle providing additional momentum – this can increase productivity and reduce abrasive consumption by up to 40% when compared with straight bore nozzles.

Airblast offers a full selection of nozzles with various orifice sizes, nozzle lengths, insert and liner materials. Contact Airblast to discuss which nozzle is most suitable for your specific application.

## ABSCX - Silicon Carbide Long Venturi Nozzles w/Polyurethane jacket and large 50 mm thread

Part no.	Description	Orifice	Length	Inlet
2048300	ABSCX – 5/50 Silicon Carbide Nozzle	8,0 mm	145 mm	32 mm
2048400	ABSCX – 6/50 Silicon Carbide Nozzle	9,5 mm	170 mm	32 mm
2048500	ABSCX – 7/50 Silicon Carbide Nozzle	11,0 mm	200 mm	32 mm
2048600	ABSCX – 8/50 Silicon Carbide Nozzle	13,0 mm	230 mm	32 mm

### COMPATIBILITY GUIDE

No.	Nozzle Orifice	Recommended range		Minimum Blast Machine capacity	Minimum Pipe ID	Blast Hose ID	Minimum Air Hose ID
		m <sup>3</sup> /min	CFM				
3	5.0 mm	1.27 - 2.29	45 - 81	60 ltr.	1"	¾"	1"
4	6.5 mm	2.29 - 3.88	81 - 137	60 ltr.	1"	1" - 1¼"	1¼"
5	8.0 mm	3.88 - 5.55	137 - 196	100 ltr.	1"	1" - 1¼"	1¼"
6	9.5 mm	5.55 - 7.19	196 - 254	200 ltr.	1¼"	1¼"	1½"
7	11.0 mm	7.19 - 9,57	254 - 338	200 ltr.	1¼"	1¼" - 1½"	2"
8	12.5 mm	9.57 - 15.52	338 - 548	200 ltr.	1¼"	1½"	2"

**Note:** Best performance is obtained when sizes of nozzle, blast machine piping, blast hose and air hose are properly matched.

- m<sup>3</sup>/min and CFM range is based on blasting at 7 bar (100 psi) for the life of the nozzle.
- Blast machine capacity should allow 20 to 30 minutes of blasting.
- Hose ID should be three to four times the size of the nozzle orifice.

### NOZZLE PRESSURE / NOZZLE DIAMETER GUIDE

ORIFICE (mm) (")	NOZZLE PRESSURE / NOZZLE DIAMETER GUIDE												REQUIRED AIR	REQUIRED ABRASIVE	REQUIRED POWER	CFM Lbs./hr. hp	m <sup>3</sup> /min KG/hr.* kw
	60 PSI	4.2 BAR	70 PSI	4.9 BAR	80 PSI	5.6 BAR	90 PSI	6.3 BAR	100 PSI	7.0 BAR	120 PSI	8.5 BAR					
5.0 mm 3/16"	30.0	0.85	33.0	0.93	38.0	1.08	41.0	1.16	45.0	1.27	58.0	1.64	REQUIRED AIR	CFM	m <sup>3</sup> /min		
	171.0	77.00	196.0	89.00	216.0	96.00	238.0	108.00	264.0	120.00	375.0	170.00	REQUIRED ABRASIVE	Lbs./hr.	KG/hr.*		
	7	5.3	8	5.6	9	6.4	10	7.1	10	7.5	12	9.0	REQUIRED POWER	hp	kw		
6.5 mm 4/16"	54.0	1.53	61.0	1.73	68.0	1.93	74.0	2.10	81.0	2.29	105.0	2.97	REQUIRED AIR	CFM	m <sup>3</sup> /min		
	312.0	141.00	354.0	160.00	408.0	185.00	448.0	203.00	494.0	224.00	660.0	300.00	REQUIRED ABRASIVE	Lbs./hr.	KG/hr.*		
	12	9.0	14	10.1	16	11.6	17	12.4	18	13.5	22	16.2	REQUIRED POWER	hp	kw		
8.0 mm 5/16"	89.0	2.52	101.0	2.86	113.0	3.20	126.0	3.57	137.0	3.88	160.0	4.53	REQUIRED AIR	CFM	m <sup>3</sup> /min		
	534.0	242.00	604.0	274.00	672.0	305.00	740.0	335.00	850.0	385.00	1.050.0	476.00	REQUIRED ABRASIVE	Lbs./hr.	KG/hr.*		
	20	15.0	23	19.1	26	20.2	28	21.0	31	22.9	37	27.5	REQUIRED POWER	hp	kw		
9.5 mm 6/16"	126.0	3.57	143.0	4.05	161.0	4.56	173.0	4.90	196.0	5.55	235.0	6.65	REQUIRED AIR	CFM	m <sup>3</sup> /min		
	764.0	346.00	864.0	392.00	960.0	425.00	1.052.0	477.00	1.152.0	523.00	1.475.0	669.00	REQUIRED ABRASIVE	Lbs./hr.	KG/hr.*		
	28	21.0	32	24.0	36	27.0	39	28.9	44	33.0	52	39.6	REQUIRED POWER	hp	kw		
11.0 mm 7/16"	170.0	4.81	184.0	5.21	217.0	6.14	240.0	6.80	254.0	7.19	315.0	8.92	REQUIRED AIR	CFM	m <sup>3</sup> /min		
	1.032.0	468.00	1.176.0	533.00	1.312.0	595.00	1.448.0	657.00	1.584.0	719.00	2.050.0	930.00	REQUIRED ABRASIVE	Lbs./hr.	KG/hr.*		
	38	28.5	44	32.6	49	36.4	54	40.1	57	42.4	69	50.9	REQUIRED POWER	hp	kw		
12.5 mm 8/16"	224.0	6.34	252.0	7.14	280.0	7.93	309.0	8.75	338.0	9.57	410.0	11.61	REQUIRED AIR	CFM	m <sup>3</sup> /min		
	1.336.0	606.00	1.512.0	686.00	1.680.0	762.00	1.856.0	842.00	2.024.0	918.00	2.650.0	1.202.00	REQUIRED ABRASIVE	Lbs./hr.	KG/hr.*		
	50	37.5	56	42.0	63	46.9	69	51.8	75	56.3	90	67.6	REQUIRED POWER	hp	kw		

Chart shows calculated consumption rates of air and abrasive for new nozzles. When selecting a compressor add 50% to above figures to allow for normal nozzle wear and friction loss.

\* Based on abrasive density of 1,5 kgs. per liter.

**NOTE:** Figures may vary depending upon working conditions. To maintain desired air pressure as nozzle orifice wears, air consumption increases. The effects of nozzle wear on air consumption must be considered when selecting nozzles and the compressors that support them.